



H 66310 Difutex 10

Product	Scrim-reinforced, vapour permeable, wind-proof synthetic vapour control layer, very easy to install, for interiorwork and loft conversions. Application as single layer or in combination with vapour permeable underlays.
Top side	PP-fabric
Bottom side	PE-Foil (inside)
Intended use	• Vapour control layer for interiorworks and loft conversion
Standard	EN 13948
Application	Invisible mechanical fixing Overlaps and connection parts need to be bonded air-tight with Difutex EKB I 60 or rather masonry-adhesive Difutex MA-K
Packaging	50 rolls of 50 m x 1,5 m = 3750 m ² per pallet

Characteristics	Testing method	Unit	Result
Length	EN 1848-1	m	50
Width	EN 1848-1	m	1,5
Straightness	EN 1848-1	mm/10 m	< 20
Mass per unit area	EN 1849-1	g/m ²	110 (+10 / -3)
Thickness	EN 1849-1	mm	0,6 (±0,1)
Fire classification	EN 13501-1	Klasse	E
Watertightness	EN 13859	kPa	2
sd-value	EN 1931	m	25 (+15 / -7)
Artificial aging - sd-value	EN 1931		bestanden
Tensile force long./trans.	EN 12311-1	N/50 mm	> 250 / > 250
Elongation (long./trans.)	EN 12311-1	%	> 20 / > 15
Resistance to tearing (long./trans.)	EN 12310-1	N	> 150 / > 150
Dimensional stability	EN 1107-1	%	NPD
Flexibility at low temperatures	EN 1109	°C	-40
Resistance to air permeability	EN 13859-1		NPD
Artificial aging - Behaviour to alkali	EN 13984, C	%	NPD

NPD = No performance determined

The product is free of hazardous substances.

System components

- H66322 Difutex EKB I60
- H66351 Difutex MA-K



EKB I60



MA-K

The declared data are indices based on the statistical quality control and refer to the date of production. Consider state of the art, standards, legal provisions and guidelines for the suitability of the mentioned field of application and application method. All specifications are without obligation. The user must assess the suitability of the product for the particular purpose and ensure the user's access to the current version of the product data sheet.

Subject to alteration without notice.

Storage conditions: The products have to be stored in original packaging, being protected from direct sun light, UV-beams and extreme conditions like heat, frost, moisture, etc. During cold season store the products in a frost-free area (+5°C) for 12 hours before application.

Development, Production and Sales of our products according to ISO 9001.