

H 70025

Büscherit Voranstrich Speed BVS 25

Product Low viscous bitumen based primer V_R for roof and basement waterproofing

- Cold applicable
- · Insensitive to frost
- · Low odour and phenol-free
- Very good adhesion on the subconstruction
- · Extreme short drying time
- · Low content of solvents

Intended use

Primer and bonding agent on concrete, light concrete, flush-jointed masonry, cement plaster or metal for roof- and basement waterproofing with bituminous membranes, as well as bituminous protective coating

Application

The surface needs to be solid, moderate rough, clean and dry.

BÜSCHERIT PRIMER SPEED BVS 25 has to be applied by brushing or rolling, at a surface temperature of min. +5°C. In case of multi layer application, each layer needs to be dry before the application of the next layer.

The primer is applicable in outside areas and well ventilated areas. Fresh applied primer can be damaged or rather washed off due to heavy rain.

Informationen for safe storage and handling see the actual material safety data sheet.

Consumption $0.2 - 0.3 \text{ l/m}^2$ per layer, depending on surface conditions

Drying time Quick drying, app. 20 - 45 minutes, depending on surface conditions and temperature

Best before Minimum 2 years storable in original, unopened, undamaged sealed packaging.

Packaging 25 liter drums

The declared data are indices based on the statistical quality control and refer to the date of production. Consider state of the art, standards, legal provisions and guidelines for the suitability of the mentioned field of application and application method. All specifications are without obligation. The user must assess the suitability of the product for the particular purpose and ensure the user's access to the current version of the product data sheet.

Subject to alteration without notice.

Storage conditions: The products have to be stored in original packaging, being protected from direct sun light, UV-beams and extreme conditions like heat, frost, moisture, etc. During cold season store the products in a frost-free area (+5°C) for 12 hours before application.

Development, Production and Sales of our products according to ISO 9001.

Issue date: 13.01.2024 Page 1 / 1