

H 93xxx DCD Ideal EPS-W 25 (EPS 120)

Intended use	• below ballast, acc. ÖNORM B 6000
Formats	1000*1000 mm, 1000*500 mm
Code for identification	EPS EN 13163 L(3)-W(3)-T(2)-S(5)-P(5)-DS(N)2-DS(70,-)3-DLT(1)5-CS(10)120-BS170

Characteristics	Unit	Result
Declared thermal conductivity λ_D	W/mK	0,036
Compressvie stress at 10% compression	kPa	120
Permanent compressvie stress at 2% compression	kPa	25
Bending strength	kPa	170
Reaction to fire test	Klasse	E

The declared data are indices based on the statistical quality control and refer to the date of production. Consider state of the art, standards, legal provisions and guidelines for the suitability of the mentioned field of application and application method. All specifications are without obligation. The user must assess the suitability of the product for the particular purpose and ensure the user's access to the current version of the product data sheet.

Subject to alteration without notice.

Storage conditions: The products have to be stored in original packaging, being protected from direct sun light, UV-beams and extreme conditions like heat, frost, moisture, etc. During cold season store the products in a frost-free area (+5°C) for 12 hours before application.

Development, Production and Sales of our products according to ISO 9001.