

H 94310

Gummigranulatbahn 10 mm GGB 10

| | |
|---------------------|---|
| Product | Recycled rubber granule membrane, polyurethan-binded |
| Colour | black / coloured spots |
| Surface | Granulated |
| Intended Use | Protection against mechanical damages of high grade waterproofing (flat- and green roof, terraces, parking decks, bridges and trafficed areas, horticulture and landscape gardening, etc.) |
| Application | Loose laid with min. 10 cm overlap. The rubber granule membrane has to be protected against UV-beams. |
| Packaging | 11 rolls of 6 x 1,25 m = 82,5 m ² per pallet (7,5 m ² per roll) |

| Characteristics | Testing method | Unit | Result |
|--|----------------|-------------------|---|
| Length | | m | 6 (± 1%) |
| Width | | mm | 1250 (± 2%) |
| Thickness | | mm | 10 (± 10%) |
| Weight per roll | | kg | 57 (± 7%) |
| Reaction to fire test | EN 13501-1 | Klasse | E |
| Tensile force | EN ISO 1798 | N/mm ² | 0,42 (± 10%) |
| Elongation at break | EN ISO 1798 | % | 46 (± 10%) |
| Load at 10% compression | EN ISO 844 | kPa | ca. 200 |
| Resistance to static loading (Meth. B) | EN 12730 | kg | 50 |
| Resistance to dynamic load, Meth. A | EN 12691 | mm | mind. 2250 |
| Thermal resistance | | °C | -30 / +80 |
| Chemical reaction | | | bedingt gegen Säuren und Laugen beständig |
| Environmental fate | | | verrottungsbeständig und wasserverträglich |

The declared data are indices based on the statistical quality control and refer to the date of production. Consider state of the art, standards, legal provisions and guidelines for the suitability of the mentioned field of application and application method. All specifications are without obligation. The user must assess the suitability of the product for the particular purpose and ensure the user's access to the current version of the product data sheet.

Subject to alteration without notice.

Storage conditions: The products have to be stored in original packaging, being protected from direct sun light, UV-beams and extreme conditions like heat, frost, moisture, etc. During cold season store the products in a frost-free area (+5°C) for 12 hours before application.

Development, Production and Sales of our products according to ISO 9001.