

8106/002-03

Polyfin Wartungswegplatte

Intended use • Protective layer for the roofing sheet, marking of walkways

Application The walkway tiles must not be welded directly onto the waterproofing. They must be welded onto a carrier membrane that has been laid separately beforehand. The seam areas must be welded all around with hot air. The longitudinal seams can be produced using the automatic welding machine. See also the installation instructions from POLYFIN AG in the currently valid version. A distance of ≥ 4 cm must be maintained between the individual walkway tiles. It is recommended to leave an unwelded area (approx. 4 - 8 cm) in the seam on the side facing away from the slope to allow for vapor pressure equalization. Due to the effects of thermally induced length changes, the outside temperature should be at least $+10^{\circ}\text{C}$ during processing. For more detailed processing information, see the separate, supplementary processing instructions.

Packaging rolls of $m \times m = m^2$ per pallet

Characteristics	Testing method	Unit	Result
Visible defects	EN 1850-2		Keine
Length	EN 1848-2	mm	ca. 785
Width	EN 1848-2	mm	ca. 590
Thickness	EN 1849-2	mm	ca. 8 mm - 8,5 einsch. Profilierung (ca. 4 mm)
Mass per unit area	EN 1849-2	kg/Platte	ca. 3
Reaction to fire test	EN 13501-1	Klasse	E
Slip resistance	DIN 51130		R 10
	DIN 51130		V 10



The declared data are indices based on the statistical quality control and refer to the date of production. Consider state of the art, standards, legal provisions and guidelines for the suitability of the mentioned field of application and application method. All specifications are without obligation. The user must assess the suitability of the product for the particular purpose and ensure the user's access to the current version of the product data sheet.

Subject to alteration without notice.

Storage conditions: The products have to be stored in original packaging, being protected from direct sun light, UV-beams and extreme conditions like heat, frost, moisture, etc. During cold season store the products in a frost-free area ($+5^{\circ}\text{C}$) for 12 hours before application.

Development, Production and Sales of our products according to ISO 9001.